

Jul., 2025

Ionbond Austria Product-Portfolio



IHI GROUP



PVD Thin Film Coatings

General Classification	Wear-Resistance		Wear-Resistance, Thermal Resistance	Tribol. Friction-Reduction		
Coating	lonbond [™] 01	Ionbond [™] 30	Ionbond [™] 347	Tribobond [™] 42 DLC	Tribobond [™] 46 Me:DLC	
Coating Structure	TiN	CrN	CrON	CrN + a-C:H	CrN + a-C:H:Me WC/C	
Hardness HV	2700+/-300	1800+/-150 2800+/-400 Function Layer ~3000		Function Layer ~2000		
Coefficient of Friction (vs.steel dry)	~ 0,4	~ 0,4	~ 0,6	< 0,1 < 0,1		
Standard Thickness (µ)	2 to 4	3 to 6	3 to 7	3 to 6 3 to 6		
Coating-Temp. C°	< 350°C (< 200°C possible)	< 200°C	< 230°C	< 220°C	< 200°C	
max. temperature Resistance	500°C	800°C	> 800°C	~350°C ~350°C		
Protection against Abrasion	√ √	✓	√ √ √	 	√ √	
Protection against Adhesion	✓	✓ ✓	√ √	44	444	
Protection against Fatigue	✓	111	*** *** ***		√ √	
Color	Gold Light-Grey		Rainbow (Anthracite)	Anthracite	Anthracite	
Coating properties	Ductile coating with very good resistance of abrasion	Very ductile coating with fine structure and good resistance of abrasion, High thermic stability	fine structured coating with very good resistance against abrasion, and fatigue and espessially high thermal durability Anti-Stick-Effect against many materials	Fine structured multi-functional layer for precision components with insufficient lubrication, scuffing risk and high abrasive wear	Very well to use for precision parts with insufficient lubrication and seizure risk.	
Application	Hydrl. components, tools mechanical components, valves		Tools wiht the need of high thermal durability as for example casting components with high needs to thermal durability or/and abrasion Best solution for a lot of plastic inj. molding appl. Engine components, bearings, hydrl. Components, fuel injection systems, bearings, various Mechanical components		Engine components, gears, bearings, hydrl. Components, racing, shafts,	









For medical / food-contact applications, FDA approval

Coating	Medthin [™] 01 Ionbond [™] 01	Ionbond [™] 347	Medthin [™] 30 Ionbond [™] 30	Medthin [™] 42 Ionbond [™] 42	Ionbond [™] 36	
Coating structure	TiN	CrON	CrN	a-C:H DLC	CrWCC	
Technology	PVD	PVD	PVD	PVD/PACVD	PVD	
Hardness HV	2900 +/-300	2800+/-400	1800+/-150	2400 +/-400	1400+/-400	
Coefficient of friction	~ 0,4	~ 0,5	~ 0,4	~ 0,1	~ 0,2	
Standard thickness (μ)	1,5 - 4	3 to 7	2 - 6	1,5 - 4	1 to 3	
Coating-temp. (°C)	< 350°C (but <200°C possible)	< 230°C	< 200°C	< 220°C	< 200°C	
max. temperaure resistance	500°C	> 800°C	800°C	350°C	350°C	
Protection against abrasion	**	* * *	✓	* * *	44	
Protection against adhesion	✓	44	✓	111	44	
Reduction of light-reflection		✓	✓	* *	111	
Easy cleaning	11	111	44	111	44	
Color	gold	Rainbow (Anthracite)	silver grey	black grey- glossy	deep black	
Application	Very wear resistant, builds very good chemical barrier; gives your instuments a high value look	very good resistance against abrasion, and fatigue espessially high thermal durability Anti-Stick-Effect against many materials	high wear resistant, builds very good chemical barrier	features very low friction, an ultra smooth surface and extremely high wear resistance.	Decorative but also functional coating, scratch protection, friction reduction and -90% light reflection!	
Usage	Implants, Instruments, orthopädic implants; trauma and fixation components made of titanium and stainless steels For food-contact applications	Components, tools or instruments with the need of high thermal durability as or/and abrasion Best solution for a lot of "plastic" applications	Surgical Instruments which requires save functionality; Instruments and tools For food-contact applications	Components and instruments for spine surgery, cardiovas. device components ,guiding wires , applications where low friction and very good wear resistance is required For food-contact applications	All kinds of components, instruments or tools in the contact to the human body; for food contact applications	







Ionbond Austria GmbH; High-Tech-Park 25; A-8605 Kapfenberg; www.ionbond.com; Tel. +43 3862 33637



Decorative Functional thin film Coatings

		Color values measured on a grinded testplate		Hardness	Thickness	Coating	Coating-Temp.	
	L a b		[HV]	[µm]	[°([°C]		
Decobond [™] Gold	L 69-76	a 3-5	b 29-34	2000	0,5 to 1	<200		
Decobond [™] Light Gold	L 71-77	a 0,5-2,5	b 17-22	2000	0,5 to 1	<200		
Decobond [™] Gold Sand	L 68-73	a 3-5	b 13,5-17	2000	0,5 to 1	<200		
Decobond [™] Champagne	L 69-74	a 1-3	b 8-12	2000	0,5 to 1	<200	Ter	
Decobond [™] Light Brown	L 62-68	a 4-7	b 6-9	2000	0,5 to 1	<200	Temperature can be modified (70-200°C)	
Decobond [™] Bronze	L 67-72	a 7-9	b 21-25	2000	0,5 to 1	<200	ature	
Decobond [™] Copper	L 58-63	a 9-12	b 14-18	2000	0,5 to 1	<200	can	
Decobond TM Mocca	L 46-50	a 4-7	b 3,5-6,5	2000	0,5 to 1	<200	be m	
Decobond [™] FDE	L 53-58	a 4-6	b 12-16	2000	0,5 to 1	<200	odifie	
Decobond [™] Desert	L 56-61	a 2-5	b 6-10	2000	0,5 to 1	<200	ed (70	
Decobond [™] Platinum	L 76-81	a -0,5-0,5	b -0,5-0,5	2000	0,5 to 1	<200)-200	
Decobond [™] Smoked Silver	L 51-56	a 0-1	b 1-3	2000	0,5 to 1	<200	ငိ	
Decobond [™] Anthrazit	L 44-49	a 0-1	b 0,5-2,5	1600	0,5 to 1	<200		
Decobond [™] Black	L 30,5-35,5	a -1 - 1	b -1 - 2	1300	0,5 to 1	<200		
Decobond TM Rainbow	INTER	INTERFERENCE Color (green or blue touch possible)			0,5 to 1	<200		
Ionbond [™] 347 Anthracite "Ducro"	CrON Anthracit	CrON Anthracite (L~50) with extensive chemical and thermal resistance			1,5 bis 2,5	<200		
Applications		=	: faucets, automotive exterior and in plies, weapons, jewelry etc	nterior, fashion indus	stry, facility,			
PVD-Decobond coatings are well known for:	 Enormous Hardness, scratch resistance High resistance against chemical impacts "Metallic - HIGH TECH LOOK" Bring FUNCTION & DESIGN together 							

